




novalca

NOVABLEND PC/ABS UG

PC/ABS compounds for aesthetic parts

	T45	T65	T85	T65 F	T85 F
Izod notched impact strength, at +23 °C - J/m	300 ÷ 400	400 ÷ 500	450 ÷ 600	350 ÷ 450	350 ÷ 550
MFI 260°C/5 Kg - g/10'	15 ÷ 30	15 ÷ 25	12 ÷ 25	≥ 30	≥ 25
Vicat B120 - °C	110 ÷ 120	120 ÷ 130	≥ 130	120 ÷ 130	≥ 130
Description	Standard grade	Standard grade	Standard grade BPT 125 formulation available on demand	Improved flow grade	Improved flow grade
 UL homologation	-	T65 Y	T85 Y	-	-

Contact us to discover all our grades, and for tailor-made solutions.

NOTES

We can match tailor-made colors and special formulations on the base of customer specifications.

UV stabilized grades available on demand.

Values may be affected by coloring and pigmentation.

Discover our **NOVABLEND PC/ABS IQ portfolio, innovative, tailor made and eco-sustainable grades.**