



NOVAKRIL SAN

SAN Compounds

	UG	FV35 ES
MFI 220°C/ 10 Kg - g/10'	20 ÷ 30	3 ÷ 5
Flexural modulus - MPa	3000 ÷ 3500	10000 ÷ 11000
Vicat B120 - °C	103 ÷ 108	105 ÷ 110
Glass content - %	-	34 ÷ 36
Description	Standard grade, for injection molding of aesthetic parts	35% glass fiber reinforced grade, for extrusion of thermal break profiles

Contact us to discover all our grades, and for tailor-made solutions.

NOTES

**We can match tailor-made colors and special formulations on the base of customer specifications.
Values may be affected by coloring and pigmentation.**