



**novalca**

## **NOVABLEND PC/ASA**

PC/ASA compound with high light fastness

	<b>PC/ASA T65</b>	<b>PC/ASA T85</b>	<b>PC/ASA FR</b>	<b>PC/ASA FR F HF</b>
<b>Izod notched impact strength, at +23 °C - J/m</b>	≥ 350	≥ 350	350 ÷ 450	200 ÷ 400
<b>MFI 240°C/5 Kg - g/10'</b>	15 ÷ 25	10 ÷ 20	15 ÷ 25	30 ÷ 35
	260°C / 5 Kg	260°C / 5 Kg	240°C / 5 Kg	240°C / 5 Kg
<b>Vicat B120 - °C</b>	120 ÷ 130	≥ 130	100 ÷ 110	100 ÷ 110
<b>Flammability class UL94 vertical Thickness 1.6 mm</b>	HB	HB	V0	V0
<b>Description</b>	Standard grade	Available also with BPT 125	Standard grade	Chlorine and bromine free

**Contact us to discover all our grades, and for tailor-made solutions**

### NOTES

**We can match tailor-made colors and special formulations on the base of customer specifications.**

Values may be affected by coloring and pigmentation.