



novalca

NOVAKRAL ABS FV

ABS compounds, high performance glass reinforced grades

	FV7	FV10	FV17	FV32
Izod notched impact strength, at +23 °C - J/m	50 ÷ 70	70 ÷ 110	80 ÷ 120	70 ÷ 110
Flexural modulus - MPa	3000 ÷ 3300	4000 ÷ 4500	5200 ÷ 5700	7500 ÷ 8500
Glass content - %	6 ÷ 8	9 ÷ 11	16 ÷ 18	28 ÷ 32
Description	Standard grade	Standard grade, formulation with improved flow available on demand	Standard grade	Special grade on demand

Contact us to discover all our grades, and for tailor-made solutions

NOTES

We can match tailor-made colors and special formulations on the base of customer specifications.

UV stabilized grades available on demand.

Values may be affected by coloring and pigmentation.

Discover our NOVAKRAL ABS IQ portfolio, innovative, tailor made and eco-sustainable grades.