



**novalca**

## **NOVAMIDE PA12**

PA12 compounds for a broad range of applications

	<b>PA12 P0</b>	<b>PA12 P0 HI</b>	<b>PA12 P20</b>	<b>PA12 P40</b>	<b>PA12 FV30</b>
<b>Izod notched impact strength, at +23 °C - DRY - J/m</b>	80 ÷ 120	≥ 80	≥100	NO BREAK	≥ 80
<b>MFI 235°C/2.16 Kg - g/10'</b>	2 ÷ 8	3 ÷ 8	2 ÷ 8	2 ÷ 8	-
<b>Flexural modulus DRY - MPa</b>	1300 ÷ 1500	1000 ÷ 1300	600 ÷ 800	400 ÷ 600	5000 ÷ 6000
<b>Description</b>	Standard grade, rigid, without plasticizer	Semi-flexible, high viscosity, without plasticizer	Semi-flexible, high viscosity, plasticized	Flexible, high viscosity, plasticized	Rigid, 30% glas fiber reinforced

**Contact us to discover all our grades, and for tailor-made solutions.**

### NOTES

**We can match tailor-made colors and special formulations on the base of customer specifications.**

Values may be affected by coloring and pigmentation.