




NOVAMIDE PA66 FR FV

PA66 compounds, glass fiber reinforced flame retardant grades

	FR FV25	FR FV25 PH
Izod notched impact strength, at +23 °C - DRY - J/m	≥ 60	≥ 60
Glass content - %	24 ÷ 26	24 ÷ 26
Flammability class UL94 vertical - Thickness 1.6 mm	V0	V0
GWFI - Thickness 2 mm - °C	960	960
Flexural modulus - DRY - MPa	7000 ÷ 8000	7000 ÷ 8000
Comparative tracking index - solution A, CTI - PLC	-	1
Description	With halogenated flame retardant additives.	Flame retardant system based on red phosphorous. Available only in natural color (brick red due to red phosphorous) and in black.
 UL homologation	-	FR Y FV25 PH

Contact us to discover all our grades, and for tailor-made solutions.

NOTES

We can match tailor-made formulations on the base of customer specifications.