



novalca

NOVABLEND PA/ABS

PA/ABS compounds for automotive market

	PA/ABS UG	PA/ABS FV8
Izod notched impact strength, at +23 °C – DRY - J/m	100 ÷ 120	100 ÷ 120
Glass content - %	0	7 ÷ 9
Vicat B120 - °C	100 ÷ 110	110 ÷ 115
Flexural modulus – DRY - MPa	1800 ÷ 2000	2800 ÷ 3000
Description	Low gloss, high aesthetic, non-reinforced grade	8% glass fiber reinforced grade with good dimensional stability

Contact us to discover all our grades, and for tailor-made solutions.

NOTES

We can match tailor-made colors and special formulations on the base of customer specifications.

Values may be affected by coloring and pigmentation.