



novalca

NOVABLEND PC/ABS T88 FV

PC/ABS compounds, high performance glass reinforced grades

	T88 FV10	T88 FV13	T88 FV20	T88 FV30
Izod notched impact strength, at +23 °C - J/m	70 ÷ 110	70 ÷ 110	80 ÷ 120	70 ÷ 110
Flexural modulus - MPa	3700 ÷ 4300	4000 ÷ 4500	5200 ÷ 5700	7500 ÷ 8500
Tensile strength, stress at break - MPa	60 ÷ 70	60 ÷ 70	70 ÷ 80	80 ÷ 100
Vicat B120 - °C	≥ 130	≥ 125	≥ 130	≥ 130
Glass content - %	9 ÷ 12	12 ÷ 14	18 ÷ 22	29 ÷ 33

Contact us to discover all our grades, and for tailor-made solutions

NOTES

We can match tailor-made colors and special formulations on the base of customer specifications.

UV stabilized grades available on demand.

Values may be affected by coloring and pigmentation.

Discover our **NOVABLEND PC/ABS IQ portfolio, innovative, tailor made and eco-sustainable grades.**