



NOVARAN ASA

Compound di ASA with high light fastness

	ASA UG	ASA TR
Izod notched impact strength, at +23 °C - J/m	70 ÷ 100	70 ÷ 10
MFI 220°C/10 Kg - g/10'	4 ÷ 10	4 ÷ 8
Vicat B120 - °C	95 ÷ 100	102 ÷ 107
Flammability class UL94 vertical Thickness 1.6 mm	HB	HB
Description	For particular colors with improved flowability	Standard grade

Contact us to discover all our grades, and for tailor-made solutions

NOTES

We can match tailor-made colors and special formulations on the base of customer specifications.

Values may be affected by coloring and pigmentation.