



novalca

NOVABLEND® PC/ABS T125 FR

PC/ABS compound,
non reinforced,
flame retardant grade

FR: flame retardant, V0 at 1.6 mm

Thermal properties: **T125FR**, Vicat (B120) 123 ÷ 127°C – for injection molding of parts with superior thermal properties and flammability.

Color: available in a limited range of colors.

RECOMMENDED PROCESSING PARAMETERS FOR INJECTION MOLDING					
DRYING CONDITIONS	BARREL TEMPERATURE	MOULD TEMPERATURE			
90 ÷ 100 °C x 3 ÷ 4 hours Recommended moisture level after drying ≤0.02%	240 ÷ 270 °C Standard melt temperature: 250°C	70 ÷ 90 °C			
PACKAGING					
25 Kg Bags, 1000 Kg Octabins, 750 Kg Boxes					

PROPERTIES	METHOD	UNIT	TYPICAL VALUES
PHYSICAL			
Density	ASTM D792	gr/cm ³	1.19
Humidity Absorption (equilibrium, in air, +23°C – 50% RH)	INTERNAL METHOD	%	0.20
Mould Shrinkage	INTERNAL METHOD	%	0.4 ÷ 0.7
Melt Flow Index MFI (240 °C - 5 Kg)	ASTM D1238	g/10'	12
MECHANICAL			
Tensile strength: stress at yield	ASTM D638	MPa	60
strain at break	ASTM D638	%	≥ 50
Flexural modulus	ASTM D790	MPa	2500
IZOD notched impact strength, at 23 °C	ASTM D256	J/m	400
Specimen dimensions 62.5 mm x 12.7 mm x 3.2 mm			
THERMAL			
VICAT softening temperature at 49 N-120 °C/h	ASTM D1525/B	ISO 306/B	°C
Ball pressure test - BPT		IEC 60695-10-2	°C
ELECTRICAL			
Surface resistivity	ASTM D257	IEC 60093	Ohm
Dielectric strength – at 1 mm	ASTM D149	IEC 60243-1	kV/mm
Dielectric constant at 10 ⁶ Hz	ASTM D150	IEC 60250	-
Dissipation factor - 10 ⁶ Hz	ASTM D150	IEC 60250	-
Comparative tracking index (solution A, CTI)	VDE 0303-P1	IEC 60112	V
FLAMMABILITY			
Flammability UL94 (thickness 3.2 mm)	UL 94	Class	V0
Flammability UL94 (thickness 1.6 mm)	UL 94	Class	V0
Glow wire flammability GWFI (thickness 3.2 mm)	IEC 60695-2-12	°C	960
Glow wire flammability GWFI (thickness 2 mm)	IEC 60695-2-12	°C	960

Our technical data are provided for guidance purpose only for natural color compound and are based on average values. The data are not meant to be used for specification or warranted purposes. Values may be affected by the design of the mold/die, the processing conditions and coloring/pigmentation of the product. Unless specified to the contrary, the data have been established on standardized test specimens at room temperature. All technical information is subject to continuous update, so the customer shall always ensure that the latest release of technical information is at his own disposal. It is the customer's responsibility to inspect and test our products in order to determine to his own satisfaction whether they are suitable for his intended uses and applications or used in conjunction with third-party materials. Unless specifically stated with reference to the specific color code, the products mentioned herein are not suitable for applications in the pharmaceutical, medical, dental and toys sectors, in contact with foodstuff or for potable water transportation.

Updating: January 2025

Printing date: 19 December 2025