



novalca

# NOVABLEND® PC/ABS T88 FV20

PC/ABS compound,  
glass fiber reinforced grade

T88: high heat grade  
FV20: 20% glass fiber reinforced grade

Colour: available in natural and in black, and in specific grey shades on request -  
for injection molding of automotive components, industrial and electrical articles.

RECOMMENDED PROCESSING PARAMETERS FOR INJECTION MOLDING					
DRYING CONDITIONS	BARREL TEMPERATURE	MOULD TEMPERATURE			
95 ÷ 110 °C x 3 ÷ 4 hours Recommended moisture level after drying ≤0.02%	260 ÷ 280 °C Standard melt temperature: 270 °C	70 ÷ 100 °C			
<b>SHRINKAGE:</b> Shrinkage is affected by the geometry and the wall thickness of the molded part by the position and size of the gate and by the processing parameters. In addition, glass-fiber reinforced products show a significant difference in the shrinkage perpendicular and parallel to the flow direction.					
<b>PACKAGING</b>					
25 Kg Bags, 1000 Kg Octabins, 750 Kg Boxes					

PROPERTIES	METHOD	UNIT	TYPICAL VALUES
<b>PHYSICAL</b>			
Density	ASTM D792	gr/cm <sup>3</sup>	1.29
Humidity Absorption – (Equilibrium value, in air, 23°C, 50% RH)	INTERNAL METHOD	%	0.25
Mould Shrinkage	INTERNAL METHOD	%	0.2 ÷ 0.5
Reinforcing filler	INTERNAL METHOD	%	20
<b>MECHANICAL</b>			
Tensile strength: stress at break	ASTM D638	MPa	80
strain at break	ASTM D638	%	2.5
Flexural modulus	ASTM D790	MPa	6000
IZOD notched impact strength, at 23 °C Specimen dimensions 62.5 mm x 12.7 mm x 3.2 mm	ASTM D256	J/m	85
<b>THERMAL</b>			
VICAT softening temperature at 49 N-120 °C/h	ASTM D1525/B	°C	132
<b>ELECTRICAL</b>			
Surface resistivity	ASTM D257	Ohm	1E16
Dielectric strength	ASTM D149	KV/mm	35
Dielectric constant at 10 <sup>6</sup> Hz	ASTM D150	IEC 60250	-
Dissipation factor -10 <sup>6</sup> Hz	ASTM D150	IEC 60250	-
Comparative tracking index (solution A, CTI)	VDE 0303-P1	IEC 60112	V
<b>FLAMMABILITY</b>			
Flammability UL94 (thickness 3.2 mm)	UL 94	Class	HB
Flammability UL94 (thickness 1.6 mm)	UL 94	Class	HB
Burning rate FMVSS302 (thickness 2.2/ 3.2 mm)	ISO 3795	Mm/min	passed

Our technical data are provided for guidance purpose only for natural color compound and are based on average values. The data are not meant to be used for specification or warranted purposes. Values may be affected by the design of the mold/die, the processing conditions and coloring/pigmentation of the product. Unless specified to the contrary, the data have been established on standardized test specimens at room temperature. All technical information is subject to continuous update, so the customer shall always ensure that the latest release of technical information is at his own disposal. It is the customer's responsibility to inspect and test our products in order to determine to his own satisfaction whether they are suitable for his intended uses and applications or used in conjunction with third-party materials. Unless specifically stated with reference to the specific color code, the products mentioned herein are not suitable for applications in the pharmaceutical, medical, dental and toys sectors, in contact with foodstuff or for potable water transportation.

Updating: January 2025 Printing date: 19 December 2025